

Figure: 16 TAC §4.259(d)

Engineering and Environmental Standards for Recyclable Product to be Used as Road Base		
PARAMETER	LIMITATION	METHOD
Arsenic	Less than 5.000 mg/l	EPA Method 1312, Synthetic Leaching Procedure (SPLP)
Barium	Less than 100.00 mg/l	
Cadmium	less than 1.00 mg/l	
Chromium (total)	less than 5.00 mg/l	
Lead	less than 5.00 mg/l	
Mercury	less than 0.20 mg/l	
Selenium	less than 1.00 mg/l	
Silver	less than 5.00 mg/l	
Zinc	less than 5.00 mg/l	
Benzene	less than 0.50 mg/l	
Chlorides	less than 700.00 mg/l	LDNR leachate test method 1:4 Solid Solution
TPH	less than 100 mg/l	
pH	6 to 12.49 Standard Units	
Minimum compressive strength	35 psi	A Texas Department of Transportation approved procedure appropriate for testing and evaluating a material for compressive strength.